

UL 94V0 TESTING
FOR
COTE-L INDUSTRIES, INC.
ON POLYPROPYLENE FOAM COATED
WITH TWO COATS OF CEASEFIRE
VTEC #100-2349
TESTED: FEBRUARY 17, 2006



VTEC Laboratories Inc.

February 17, 2006

Client: COTE-L Industries, Inc.
1542 Jefferson Street
Teaneck, NJ 07666

Attention: Mr. Avi Aviner

Subject: UL 94V0 Flammability Testing

Material Tested:

Manufacturer:	COTE-L Industries, Inc.
Product Description:	Polypropylene Foam coated with 2 coats of Ceasefire
Size:	285mm x 13mm x 10mm
Color:	Gray
Number of Specimens:	5 conditioned; 5 unconditioned
Surface:	Smooth
Material Description:	by VTEC and Manufacturer
Date of Selection:	January 2006
Purpose of Test:	Flammability of plastic materials
Method of Sample Mounting:	Standard. The sample was clamped 125mm from the end exposed to the flame.

Test Results:

Preconditioned at 23°C for 48 Hours


Specimen #	(t1) secs.	(t2) secs.	(t1+t2) secs.	(t3) secs.	(t2+t3) secs.	Burn to Holding Clamp	Cotton Ignition
1	0	0	0	0	0	NO	NO
2	0	0	0	0	0	NO	NO
3	0	0	0	0	0	NO	NO
4	0	0	0	0	0	NO	NO
5	0	0	0	0	0	NO	NO
TOTAL:	0	0	0	0	0		

Preconditioned at 70°C for 168 Hours

Specimen #	(t1) secs.	(t2) secs.	(t1+t2) secs.	(t3) secs.	(t2+t3) secs.	Burn to Holding Clamp	Cotton Ignition
1	0	0	0	0	0	NO	NO
2	0	0	0	0	0	NO	NO
3	0	0	0	0	0	NO	NO
4	0	0	0	0	0	NO	NO
5	0	0	0	0	0	NO	NO
TOTAL:	0	0	0	0	0		

Based on the above results, the material provided met the passing criteria for a UL 94V-0 classification.


Neil Schultz
Executive Director


Amirudin Rahim
Technical Director

Disclaimer: This is a factual report of the results obtained from the laboratory test of sample products. The results may be applied only to the products tested and should not be construed as applicable to other similar products of the manufacturer. The report is not a recommendation or disapprobation by VTEC Laboratories, Inc. of the material tested. While this report may be used for obtaining product acceptance, it may not be used in advertising.

Notice: VTEC Laboratories Inc. will not be liable for any loss or damage resulting from the use of the data in this report, in excess of the invoice. This report pertains to the sample tested only. Such report shall not be interpreted to be a warranty, either expressed or implied as to the suitability or fitness of said sample for such uses or applications, as the party contracting for the report may apply such sample.